

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C08F 20/12, C09J 4/02</p>	<p>A1</p>	<p>(11) International Publication Number: WO 97/17383 (43) International Publication Date: 15 May 1997 (15.05.97)</p>
<p>(21) International Application Number: PCT/US96/15706 (22) International Filing Date: 30 September 1996 (30.09.96) (30) Priority Data: 06/554,663 7 November 1995 (07.11.95) US (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (72) Inventor: DEVINY, E., John; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (74) Agents: O'SHAUGHNESSY, Christine, T. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p>	<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>	
<p>(54) Title: INITIATOR SYSTEM AND ADHESIVE COMPOSITION MADE THEREWITH</p>		
<p>(57) Abstract</p> <p>Systems for initiating the polymerization of acrylic monomers comprising (1) organoborane amine complexes and (2) decomplexers comprising at least one anhydride group. Adhesive compositions prepared from the initiator systems advantageously exhibit low levels of mobile constituents, excellent solvent resistance, and good adhesion to low energy surfaces.</p> <p style="text-align: center;"><i>Same priority as 5,883,208</i></p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LT	Lithuania	SK	Slovakia
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	SZ	Swaziland
CS	Czechoslovakia	MC	Monaco	TD	Chad
CZ	Czech Republic	MD	Republic of Moldova	TG	Togo
DE	Germany	MG	Madagascar	TJ	Tajikistan
DK	Denmark	ML	Mali	TT	Trinidad and Tobago
EE	Estonia	MN	Mongolia	UA	Ukraine
ES	Spain	MR	Mauritania	UG	Uganda
FI	Finland			US	United States of America
FR	France			UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

INITIATOR SYSTEM AND ADHESIVE COMPOSITION MADE THEREWITH


Field of the Invention

5 This invention relates generally to systems capable of initiating the
polymerization of acrylic monomers. More specifically, the invention relates to
those initiator systems comprising (1) organoborane amine complexes and (2)
decomplexers comprising at least one anhydride group. The invention further
relates to the use of these systems for initiating the polymerization of acrylic
10 monomers, as well as acrylic adhesive compositions made therewith. Adhesive
compositions having low levels of mobile constituents, excellent solvent resistance,
and good adhesion to low energy surfaces are advantageously provided.

Description of the Related Art

 Systems for initiating the polymerization of acrylic monomers to make
15 adhesive compositions are known in the art. U.S. Patent Nos. 5,106,928,
5,286,821, and 5,310,835, for example, disclose a two part initiator system that is
reportedly useful in acrylic adhesive compositions. The first part of this two part
system includes a stable organoborane amine complex and the second part includes
an activator. The activator liberates the organoborane compound by removing the
20 amine group, thereby allowing the organoborane compound to initiate the
polymerization process. Activators are also sometimes referred to as liberators or
decomplexers.

 The organoborane compound of the complex has the general formula:



25 where R, R₁ and R₂ are either alkyl groups having 1 to 10 carbon atoms or phenyl
groups. Useful amine compounds for the complex include n-octylamine, 1,6-
diaminohexane, diethylamine, dibutylamine, diethylenetriamine, dipropylenediamine,
ammonia, 1,3-propylenediamine, and 1,2-propylenediamine.

U.S. Patent No. 5,286,821 reports that suitable activators for liberating the organoborane compound include aldehydes having the general structure:



wherein R is alkyl of 1 to 10 carbon atoms or aryl having 6 to 10 carbon atoms and x is 1 to 2. Examples include benzaldehyde, o-, m-, p-nitrobenzaldehyde, 2,4-dichlorobenzaldehyde, p-tolylaldehyde, and 3-methoxy-4 hydroxybenzaldehyde.

U.S. Patents 5,310,835 and 5,106,928 reports that suitable activators also include organic acids having the structure:



wherein R is H, alkyl, or alkenyl having 1 to 8 carbon atoms. Examples include acrylic acid, methacrylic acid, benzoic acid, and p-methoxybenzoic acid.

Fujisawa, Imai, and Mashuhara also describe a system for initiating the polymerization of methyl methacrylate. See Reports of the Institute for Medical and Dental Engineering, 3, 64 (1969). The system comprises a trialkylborane amine complex and an activator such as the chloride of methacrylic or n-butane sulfonic acid, terephthalic acid chloride, benzoyl chloride, p-toluene sulfonic acid chloride, benzene sulfonic acid chloride, methane sulfonic acid chloride, toluene diisocyanate, adipic acid chloride, o-tolyl isocyanate, acetyl chloride, and anhydrous acetic acid. The initiator system is reportedly useful in providing fast curing resins for dental applications.


Activators (sometimes also referred to as decomplexers) liberate the organoborane compound by bonding (either covalently or ionically) to the amine to form an activator-amine constituent. Most activator-amine constituents remain in the adhesive composition as a mobile constituent that is not incorporated into the polymerized adhesive per se. In general, mobile constituents in adhesive compositions may cause performance problems when, for example, they migrate to the surface of the adhesive thereby disrupting the bond interface. Mobile constituents are also susceptible to attack by solvents, thereby making the adhesive composition less suitable for applications where exposure to solvents is unavoidable.

A need exists for initiator systems which provide acrylic adhesive compositions having reduced levels of mobile constituents and improved solvent resistance. Such adhesives are less susceptible to performance problems due to migration of mobile constituents to the bond interface and can also be used in various manufacturing applications where adhesives are exposed to organic vapors, oils, fuels, and other solvents such as methylethylketone, tetrahydrofuran, and the like.


SUMMARY OF THE INVENTION

This invention provides systems capable of initiating the polymerization of acrylic monomers. More specifically, the invention provides initiator systems comprising (1) an organoborane amine complex and (2) a decomplexer comprising at least one anhydride group. The term "decomplexer" means a compound capable of liberating the organoborane compound, thereby allowing the organoborane to initiate the polymerization process. Decomplexers are also sometimes referred to as "activators" or "liberators." As used herein, each of these terms has the same meaning. In the present invention, the anhydride group of the decomplexer is capable of forming a covalent bond with the amine portion of the organoborane amine complex to liberate the organoborane compound.

The decomplexer of the invention comprises at least one anhydride group. Preferably, the anhydride has one of the following structures:



or



Each of the R₁ and R₂ groups may independently be an aliphatic group (i.e., a straight- or branched-chain arrangement of carbon atoms falling into one of three subgroups, namely, alkane, alkene and alkyne groups); a cycloaliphatic group (i.e., a

non-aromatic cyclic hydrocarbon structure); or an aromatic group (i.e., a cyclic hydrocarbon structure that is fully unsaturated). Of these three, aliphatic and aromatic groups are preferred. Preferred aliphatic groups comprise 1 to 17 carbon atoms, more preferably 2 to 9 carbon atoms. Preferred aromatic groups include benzene and benzene substituted with aliphatic groups comprising 1 to 4 carbon atoms.

R_3 is a divalent organic radical that completes a cyclic structure with the anhydride group to form, for example, a 5 or 6 member ring. The term "divalent organic radical" means an organic moiety wherein the available valencies are on carbon atoms. R_3 may be substituted with aliphatic, cycloaliphatic or aromatic groups, preferably aliphatic groups comprising 1 to 12, more preferably 1 to 4, carbon atoms. R_3 may also contain a heteroatom such as oxygen or nitrogen with the proviso that the heteroatom is not adjacent to the anhydride functionality. R_3 may also be part of a fused ring structure. The fused ring structure may be cycloaliphatic or aromatic. The term "aromatic" in reference to a fused ring structure means that at least one carbonyl group is attached to an aromatic group. The term "cycloaliphatic" is intended to include all other non-aromatic fused ring structures. The fused ring may further be substituted with aliphatic groups, preferably those groups having 1 to 4 carbon atoms, most preferably 1 carbon atom.

The organoborane amine complex of the system of the invention comprises an amine portion and an organoborane portion. The amine portion of the complex may comprise one or more amine groups. The anhydride group of the decomplexer reacts with the amine portion of the organoborane amine complex to form a decomplexer-amine reaction product. The organoborane is thereby liberated whereupon it is capable of initiating polymerization of the acrylic monomer(s).

Preferably, the decomplexer comprises at least one free radically polymerizable group that is capable of forming a covalent bond with acrylic monomer. In this case, the decomplexer-amine reaction product is capable of forming covalent bonds with acrylic monomer(s) and can be incorporated into the

polymerized adhesive per se. This results in a reduced level of mobile constituents (i.e., those materials capable of migrating or diffusing through the cured adhesive).

Even more preferably, the decomplexer reacts with the amine portion of the organoborane amine complex to form a decomplexer-amine reaction product
5 comprising more than one free radically polymerizable group. In this case, the decomplexer not only provides a reduced level of mobile constituents, but also provides polymerized adhesive compositions having good solvent resistance.

As stated previously, the system of the invention can be used to initiate the polymerization of acrylic monomer(s). Consequently, the invention also relates to a
10 polymerizable acrylic composition that comprises at least one acrylic monomer, an effective amount of an organoborane amine complex, and an effective amount of the decomplexer of the invention for liberating the organoborane to initiate polymerization of the at least one acrylic monomer.

A wide variety of acrylic monomers may be used, for example,
15 monofunctional acrylate ester, monofunctional methacrylate ester, substituted derivatives of the foregoing, and blends of the foregoing.

Acrylic compositions of the invention are uniquely useful in providing adhesives, and adhesive compositions of the invention advantageously provide reduced levels of mobile constituents, excellent solvent resistance, and adhesion to
20 low surface energy plastics such as polyethylene and polytetrafluoroethylene. The term "low energy surface" means those materials having a surface energy of less than 45 mJ/m^2 , more typically less than about $35\text{--}40 \text{ mJ/m}^2$.


In another aspect, the invention relates to a method of initiating the polymerization of an acrylic monomer, the method comprising the steps of
25 providing at least one acrylic monomer, blending the at least one acrylic monomer with the components of the polymerization initiator system according to the invention, and initiating polymerization of the at least one acrylic monomer. As indicated above, a decomplexer-amine reaction product is formed when the decomplexer is combined with the organoborane amine complex. When the
30 decomplexer-amine reaction product comprises at least one free radically polymerizable group capable of forming a covalent bond with acrylic monomer,

polymerized acrylic compositions having a reduced level of mobile constituents are advantageously provided. Furthermore, when the decomplexer-amine reaction product comprises more than one free radically polymerizable group, this method may be used to prepare a polymerized adhesive composition having improved solvent resistance.


DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Decomplexer

The decomplexer of the invention comprises at least one anhydride group. Preferably, the anhydride has one of the following structures:



or



Each of the R_1 and R_2 groups may independently be an aliphatic group (i.e., a straight- or branched-chain arrangement of carbon atoms falling into one of three subgroups, namely, alkane, alkene and alkyne groups); a cycloaliphatic group (i.e., a non-aromatic cyclic hydrocarbon structure); or an aromatic group (i.e., a cyclic hydrocarbon structure that is fully unsaturated). Of these three, aliphatic and aromatic groups are preferred. Preferred aliphatic groups comprise 1 to 17 carbon atoms, more preferably 2 to 9 carbon atoms. Preferred aromatic groups include benzene and benzene substituted with aliphatic groups comprising 1 to 4 carbon atoms.


R_3 is a divalent organic radical that completes a cyclic structure with the anhydride group. The term "divalent organic radical" means an organic moiety wherein the available valencies are on carbon atoms. The cyclic structure may comprise, for example, a 5 or 6 member ring. R_3 may be substituted with aliphatic,

cycloaliphatic or aromatic groups, preferably aliphatic groups comprising 1 to 12, more preferably 1 to 4, carbon atoms. R₃ may also contain a heteroatom such as oxygen or nitrogen. R₃ may also be part of a fused ring structure. The fused ring structure may be cycloaliphatic or aromatic. The term "aromatic" in reference to a fused ring structure means that at least one carbonyl group is attached to an aromatic group. The term "cycloaliphatic" is intended to include all other non-aromatic fused ring structures. The fused ring may further be substituted with aliphatic groups, preferably those groups having 1 to 4 carbon atoms, most preferably 1 carbon atom.

Examples of useful anhydrides include propionic anhydride, methacrylic anhydride, crotonic anhydride, butyric anhydride, isobutyric anhydride, valeric anhydride, trimethylacetic anhydride, hexanoic anhydride, heptanoic anhydride, decanoic anhydride, lauric anhydride, stearic anhydride, oleic anhydride, benzoic anhydride, succinic anhydride, methylsuccinic anhydride, isobutenylsuccinic anhydride, 2,2-dimethylsuccinic anhydride, itaconic anhydride, maleic anhydride, citraconic anhydride, 2,3-dimethylmaleic anhydride, 2-octen-1-ylsuccinic anhydride, 2-dodecen-1-ylsuccinic anhydride, glutaric anhydride, 3-methylglutaric anhydride, 3,3-dimethylglutaric anhydride, 3-ethyl-3-methylglutaric anhydride, 2-phenylglutaric anhydride, diglycolic anhydride, ethylenediaminetetraacetic dianhydride, and poly(styrene-co-maleic anhydride), cyclohexanedicarboxylic anhydride, cis-1,2,3,6-tetrahydrophthalic anhydride, hexahydro-4-methylphthalic anhydride, cis-5-norbornene-endo-2,3-dicarboxylic anhydride, methyl-5-norbornene-2,3-dicarboxylic anhydride, exo-3,6-epoxy-1,2,3,6-tetrahydrophthalic anhydride, 3,3-tetramethyleneglutaric anhydride, phthalic anhydride, 4-methylphthalic anhydride, 1,8-naphthalic anhydride, diphenic anhydride, and homophthalic anhydride. These materials are commercially available from a variety of sources.


Further examples of useful anhydrides include the partial adducts of active hydrogen compounds (such as hydroxyl, amine and thiol compounds) with polyanhydrides (i.e., compounds having at least two anhydride groups such as ethylenediaminetetraacetic dianhydride and poly(styrene-co-maleic anhydride)).

The term "partial adduct" means that the resulting adduct retains at least one anhydride group after reaction with the active hydrogen containing compound. Examples of hydroxyl compounds useful for preparing the partial adducts include aliphatic alcohols such as methanol, ethanol, propanol, and butanol; higher alkane alcohols such as hexanol and octanol; ether alcohols such as 2-methoxyethanol, 2-(2-propoxy)ethanol, 2-butoxyethanol, and 2-ethoxyethanol; and alicyclic alcohols such as cyclohexylmethanol. Other hydroxyl compounds which may be used include those having the following structure:



wherein R_4 is hydrogen, methyl, ethyl or chlorine; R_5 is an alkyl group preferably having 2 to 16 carbon atoms; and X is oxygen or NR_6 wherein R_6 is hydrogen or an alkyl group preferably having 1 to 4 carbon atoms. More preferably, R_4 is hydrogen or methyl, R_5 is an alkyl group having 2 to 4 carbon atoms, and X is oxygen.

Still other active hydrogen containing compounds useful for preparing the partial adducts of the invention include the adducts of the above-mentioned hydroxylated (meth)acrylates with lactones. The adducts, hydroxyacrylate polyesters, may be represented by the following structure:



wherein R_4 , R_5 and X are defined above, R_7 is an alkyl group preferably having 2 to 11 carbon atoms, and m is an integer greater than or equal to 1. More preferably, R_4 is hydrogen or methyl, R_5 is an alkyl group having 2 to 4 carbon atoms, X is oxygen, R_7 is an alkyl group having 3 to 5 carbon atoms, and m is an integer from 1 to 4.

Examples of amine compounds useful for preparing the partial adducts include aliphatic primary amines such as ethylamine, butylamine, hexylamine, and

allylamine; aliphatic secondary amines such as diethylamine, dihexylamine, and N-methylbutylamine; aromatic primary amines such as aniline, the ortho-, meta- or para-toluidines, and xylylamines; and aromatic secondary amines such as n-alkyl anilines and toluidines. Examples of thiols include butanethiol; dodecyl mercaptan; esters of 3-mercaptopropionic acid such as isooctyl 3-mercaptopropionate; and esters of thioglycolic acid such as 2-ethylhexyl thioglycolate.

The partial adducts are typically prepared by first dissolving the polyanhydride in a solvent that is non-reactive with the polyanhydride and that provides a pourable medium for the subsequent dissolution of co-reactants.

Examples of suitable solvents include butyl acetate, toluene, xylene, tetrahydrofuran, ethylene glycol dimethyl ether and the like. Preferably, the solvent is free radically polymerizable with acrylic monomer so that once the partial adduct is made, the solution of partial adduct in solvent can be used to prepare adhesives without the need for solvent removal. Examples of solvents which are free radically polymerizable with acrylic monomer include the esters of acrylic or methacrylic acid such as butyl methacrylate, ethoxyethyl methacrylate, benzyl methacrylate, and tetrahydrofurfuryl methacrylate.

After the polyanhydride is dissolved in a solvent, a free radical inhibitor (for example, a phenolic compound such as hydroquinone monomethylether or butylated hydroxytoluene) is typically added at a level of 300-600 parts by weight per million parts by weight partial adduct. After the addition of the free radical inhibitor, the active hydrogen containing compound is added. A molar excess of the anhydride groups is necessary to achieve anhydride functionality in the resulting partial adduct. Once the active hydrogen containing compound is added, the mixture is then typically heated for a length of time (for example, 80°C to 110°C for several hours). When the reaction is complete, the mixture is cooled. If a free radically polymerizable solvent was used to carry out the reaction, the solution (with solvent) may be used to prepare adhesive compositions. Otherwise, the solvent is typically removed using various evaporation methods known in the art.

Preferably, the decomplexer comprises at least one free radically polymerizable group that is capable of forming a covalent bond with acrylic


monomer(s). In this case, the decomplexer-amine reaction product is capable of forming a covalent bond with acrylic monomer(s) and can be incorporated into the polymerized adhesive per se. This results in a reduced level of mobile constituents (i.e., those materials capable of migrating or diffusing through the cured adhesive).

5 Examples of polymerizable groups that may be present in the decomplexer of the invention include monosubstituted alkene groups, 1,1-disubstituted alkene groups, and 1,2-disubstituted alkene groups which are part of an α,β -unsaturated carbonyl structure. Examples of anhydrides that comprise such groups include itaconic anhydride, maleic anhydride, isobutenyl succinic anhydride, and methacrylic
10 anhydride.

Even more preferably, the decomplexer reacts with the amine portion of the organoborane amine complex to form a decomplexer-amine reaction product comprising more than one free radically polymerizable group. In this case, the decomplexer not only provides a reduced level of mobile constituents, but also
15 provides polymerized adhesive compositions having good solvent resistance. For example, the reaction of itaconic anhydride, maleic anhydride, isobutenyl succinic anhydride, or methacrylic anhydride with an organoborane amine complex comprising more than one amine group provides a decomplexer-amine reaction product comprising more than one free radically polymerizable group.

20 Organoborane Amine Complex

In general, complexes of the invention are complexes of organoborane and amine. Such complexes may be represented by the structure:




25 R_8 is an alkyl group having 1 to 10 carbon atoms. R_9 and R_{10} are independently selected from alkyl groups having 1 to 10 carbon atoms and phenyl-containing groups. Preferably, R_8 , R_9 and R_{10} are independently selected alkyl groups having 1 to 5 carbon atoms. Most preferably, they are the same.

The value of v is selected so as to provide an effective ratio of primary or secondary amine nitrogen atoms to boron atoms in the complex. The ratio of primary or secondary amine nitrogen atoms to boron atoms in the complex should broadly be about 0.5:1 to 4:1.


5 The amine, Am, may comprise a variety of structures, for example, any primary or secondary amine, polyamine containing a primary or secondary amine, or ammonia. When solvent resistance in the ultimate polymerized acrylic composition is desired, Am preferably comprises a polyamine.

For example, Am may be represented by the structure:



10

where R_{11} and R_{12} are hydrogen, alkyl of 1 to 10 carbon atoms, hydroxyethyl or




15


where R_{13} and R_{14} are hydrogen or alkyl of 1 to 10 carbon atoms, m is greater than 2, and n is 1 to 6. The alkyl groups in these formulae may comprise straight or branched chains. Illustrative compounds include *n*-octylamine, 1,6-diaminohexane, diethylamine, dibutylamine, dipropylenediamine, diethylenetriamine, ammonia, 1,3-propylenediamine, and 1,2-propylenediamine.

Alternatively, Am may be a polyoxyalkylenepolyamine having a structure such as

20



or



25

R_{15} , R_{16} and R_{17} are preferably alkylene groups having 1 to 10 carbon atoms which may be the same or different. More preferably, R_{15} is an alkyl group having 2 to 4 carbon atoms, R_{16} is an alkyl group of 2 or 3 carbon atoms, and R_{17} is


an alkyl group of 2 or 3 carbon atoms. R_{18} is a residue of a polyol used to prepare the polyoxyalkylenepolyamine (i.e., the organic structure that remains when the hydroxyl groups are removed). R_{18} may be branched or linear, saturated or unsaturated, and substituted or unsubstituted.

5 The value of w is ≥ 1 (more preferably about 1 to 150, and most preferably about 1 to 20). The value of x and y are ≥ 0 . The value of z is > 2 (more preferably 3 or 4).

 Examples of useful polyoxyalkylenepolyamines include polyethyleneoxidediamine, polypropyleneoxidediamine,
10 diethyleneglycolpropylenediamine, triethyleneglycolpropylenediamine, polytetramethyleneoxidediamine, and polyethyleneoxide-co-polypropyleneoxidediamine.

 Examples of useful commercially available polyoxyalkylenepolyamines include various JEFFAMINES from Huntsman Chemical Company such as the D,
15 ED, EDR, and T series diamines (e.g., D-400, D-2000, D-5000, ED-600, ED-900, ED-2001, EDR-148 and T403), as well as DCA-221 from Dixie Chemical Company.

 Alternatively, the amine, Am , may comprise the reaction product of one or more diprimary amine-terminated materials (i.e., the two terminal groups are
20 primary amine) and one or more materials containing at least two groups reactive with the primary amine (the latter may be referred to as a "difunctional primary amine-reactive" material). In this case, Am may be represented by the structure:



 in which each E group is the residue of the diprimary amine-terminated material and each L is a linking group that is the residue of the material having at least two
25 groups reactive with primary amine. The term "residue" means those portions of the diprimary amine-terminated material and the difunctional primary amine-reactive material that remain after reaction to form the polyamine adduct. The integral value of q is ≥ 0 (more preferably, it is from 0 to 5, and most preferably it is 0 or 1).

Useful diprimary amine-terminated materials (E) include alkyl diprimary amines, aryl diprimary amines, alkaryl diprimary amines, polyoxyalkylenediamines such as those represented by structure I described above, and mixtures thereof. A particularly preferred material for E is an aliphatic oxyalkylene diamine sold as
5 DCA-221 from Dixie Chemical Company.

Suitable candidates for the material having at least two groups reactive with primary amine (L) may be represented by the general structure W-R-Z, wherein W and Z are moieties independently selected from the group consisting of carboxylic acid, carboxylic acid halide, ester, aldehyde, epoxide, amino alcohol, and acrylic,
10 and R is a divalent organic radical. Most preferably W and Z are the same. A particularly preferred material for L is hexanedioldiacrylate.

Initiator System

The initiator systems of the invention are especially useful in polymerizing acrylic monomers, particularly for making polymerizable acrylic adhesives. The
15 organoborane amine complex is employed in an effective amount, which is an amount large enough to permit polymerization to readily occur to obtain a polymer (preferably, an acrylic polymer) of high enough molecular weight for the desired end use. If the amount of organoborane amine complex is too low, then the polymerization may be incomplete or, in the case of adhesives, the resulting
20 composition may have poor adhesion. On the other hand, if the amount of organoborane amine complex is too high, then the polymerization may proceed too rapidly to allow for effective mixing and use of the resulting composition. Large amounts of complex could also lead to the generation of large volumes of borane, which, in the case of an adhesive, could weaken the bondline. The useful rate of
25 polymerization will depend in part on the method of applying the composition to a substrate. Thus, a faster rate of polymerization may be accommodated by using a high speed automated industrial adhesive applicator rather than by applying the composition with a hand applicator or by manually mixing the composition.

30 Within these parameters, an effective amount of the organoborane amine complex is an amount that preferably provides about 0.03 to 1.5 weight % boron,

based on the total weight of the adhesive composition, more preferably about 0.06 to 0.60 weight % boron.

The weight % of boron in a composition is equal to the following:

$$5 \quad \frac{(\text{weight of complex in the composition}) \times (\text{weight \% of boron in the complex})}{(\text{Total weight of composition})}$$


10 The organoborane decomplexer liberates organoborane by reacting with the amine, thereby removing the organoborane from chemical attachment with the amine.

The decomplexer is employed in an effective amount; that is, an amount effective to promote polymerization by liberating organoborane from the complex but without materially adversely affecting the properties of the ultimate polymerized composition. Larger amounts of decomplexer may permit the polymerization to proceed too quickly and, in the case of adhesives, the resulting materials may demonstrate inadequate adhesion to low energy surfaces. If small amounts of decomplexer are employed, the rate of polymerization may be too slow and the monomers that are being polymerized may not adequately increase in molecular weight. However, a reduced amount of decomplexer may be helpful in slowing the rate of polymerization if it is otherwise too fast.

20 Within these parameters, the decomplexer is typically provided in an amount such that the ratio of anhydride groups to amine groups is in the range of 0.5:1.0 to 1.0:1.0. The number of amine groups includes both primary and secondary amine groups if the amine is a polyamine.

Compositions

The initiator systems of the invention are useful in providing polymerizable acrylic monomer compositions. "Acrylic monomers" are polymerizable monomers having one or more acrylic or substituted acrylic moieties, chemical groups or functionality; that is, groups having the general structure



wherein R_{19} and R_{20} are hydrogen or organic radicals, and X is oxygen or NR_{21} where R_{21} is hydrogen or an alkyl group preferably having 1 to 4 carbon atoms.

Where R_{19} and R_{20} are organic radicals, they may be the same or they may be different. Blends of acrylic monomers may also be used. The polymerizable acrylic monomer may be monofunctional, polyfunctional or a combination thereof.

The most useful monomers are monofunctional acrylate and methacrylate esters or amides and substituted derivatives thereof such as cyano, chloro, and silane derivatives as well as blends of substituted and unsubstituted monofunctional acrylate and methacrylate esters and amides. Particularly preferred monomers include lower molecular weight methacrylate esters and amides such as methyl methacrylate, ethyl methacrylate, butyl methacrylate, methoxy ethyl methacrylate, cyclohexyl methacrylate, tetrahydrofurfuryl methacrylate, N,N-dimethyl methacrylamide and blends thereof.

Acrylate esters and amides and higher molecular weight methacrylate esters and amides are less preferred for use alone, but can be especially usefully employed as modifying monomers with predominating amounts of lower molecular weight methacrylate esters and amides so as to, for example, enhance the softness or flexibility of the ultimate composition. Examples of such acrylate esters and amides and higher molecular weight methacrylate esters and amides include methyl acrylate, ethyl acrylate, isobornyl methacrylate, butyl acrylate, n-octyl acrylate, 2-ethylhexyl acrylate, 2-ethylhexyl methacrylate, decylmethacrylate, dodecyl methacrylate, tert-butyl methacrylate, acrylamide, N-methyl acrylamide, diacetone acrylamide, N-tert-butyl acrylamide, N-tert-octyl acrylamide, N-decyl methacrylamide, gamma-methacryloxypropyl trimethoxysilane, 2-cyanoethyl acrylate, 3-cyanopropyl acrylate, tetrahydrofurfuryl chloroacrylate, glycidyl acrylate, glycidyl methacrylate, and the like. Dimethylaminoethyl acrylate and dimethylaminoethyl methacrylate may also be used as modifying agents although additional organoborane liberator may be required due to the extra amine groups.

Particularly preferred are blends of any of the lower molecular weight alkyl methacrylate esters described above with alkyl acrylates having 4 to 10 carbon

atoms in the alkyl group, such as blends of methyl methacrylate and butylacrylate. Polymerizable compositions of this type may broadly comprise, based on the total weight of the composition, about 2 to 50 wt. % of the alkyl acrylate and, correspondingly, about 50 to 98 wt. % of the alkyl methacrylate.

5 Other useful monomers that can be used include di- or higher functional (meth)acrylates (for example, hexanedioldiacrylate, ethylene glycol dimethacrylate, ethylene glycol diacrylate, triethylene glycol dimethacrylate, polyethylene glycol diacrylate, tetraethylene glycol di(meth)acrylate, glycerol diacrylate, diethylene glycol dimethacrylate, pentaerythritol triacrylate, trimethylolpropane
10 trimethacrylate, as well as other polyether diacrylates and dimethacrylates).

The above-discussion of acrylic monomers is not intended to be exhaustive. Other acrylic monomers are known in the art and may be used in the present invention.

15 The compositions may further comprise a variety of optional additives. One particularly useful additive is a thickener such as medium (about 40,000) molecular weight polybutyl methacrylate which may be incorporated in an amount of about 10 to 40 weight %, based on the total weight of the composition. Thickeners may be employed to increase the viscosity of the composition to a more easily applied viscous syrup-like consistency.

20 Another particularly useful additive is an elastomeric material. These materials can improve the fracture toughness of compositions made therewith which can be beneficial when, for example, bonding stiff, high yield strength materials such as metal substrates that do not mechanically absorb energy as easily as other materials, such as flexible polymeric substrates. Such additives can be incorporated
25 in an amount of about 5% to 35% by weight, based on the total weight of the composition.

Useful elastomeric modifiers include chlorinated or chlorosulphonated polyethylenes such as HYPALON 30 (commercially available from E. I. duPont de Nemours and Co., Wilmington DE). Also useful, and even more preferred, are
30 certain graft copolymer resins such as particles that comprise rubber or rubber-like cores or networks that are surrounded by relatively hard shells, these materials often

being referred to as "core-shell" polymers. Most preferred are the acrylonitrile-butadiene-styrene graft copolymers.

In addition to improving the fracture toughness of the composition, core-shell polymers can also impart enhanced spreading and flow properties to the uncured composition. These enhanced properties may be manifested by a reduced tendency for the composition to leave an undesirable "string" upon dispensing from a syringe-type applicator, or sag or slump after having been applied to a vertical surface. Use of more than about 20% of a core-shell polymer additive is desirable for achieving improved sag-s slump resistance.

Peroxides may be optionally included (typically in an amount of about 2 % by weight or less, based on the total weight of the composition), for example, to adjust the speed at which the compositions polymerize or to complete the polymerization.

Small amounts of inhibitors such as hydroquinone monomethylether may be used, for example, to prevent or reduce degradation of the acrylic monomers during storage. Inhibitors may be added in an amount that does not materially reduce the rate of polymerization or the ultimate properties of an adhesive or other composition made therewith, typically about 100 - 10,000 ppm based on the weight of the polymerizable monomers.

Other possible additives include non-reactive colorants, fillers (e.g., carbon black), etc. provided they are dried sufficiently to reduce moisture content below about 0.1 % by weight based on the total weight of the additives.

The various optional additives are employed in an amount that does not significantly adversely affect the polymerization process or the desired properties of compositions made therewith.

Polymerizable acrylic compositions according to the invention may be used in a wide variety of ways, including as sealants, coatings, and injection molding resins. They may also be used as matrix resins in conjunction with glass and metal fiber mats such as in resin transfer molding operations. They may further be used as encapsulants and potting compounds such as in the manufacture of electrical components, printed circuit boards and the like. Quite desirably, they provide

polymerizable acrylic adhesive compositions that can bond a diverse myriad of substrates, including polymers, wood, ceramics, concrete, and primed metals.

The polymerizable compositions of the invention can be easily used as two-part adhesives. The components of the polymerizable composition are blended as would normally be done when working with such materials. The decomplexer of the polymerization initiator system is usually included in this blend so as to separate it from the organoborane amine complex, thus providing one part of the two-part composition. The organoborane amine complex of the polymerization initiator system provides the second part of the composition and is added to the first part shortly before it is desired to use the composition. The complex may be added to the first part directly or it may be predissolved in an appropriate carrier such as a small amount of methyl methacrylate.

For a two-part adhesive such as those of the invention to be most easily used in commercial and industrial environments, the ratio at which the two parts are combined should be a convenient whole number. This facilitates application of the adhesive with conventional, commercially available dispensers. Such dispensers are shown in U.S. Patent Nos. 4,538,920 and 5,082,147 and are available from Conprotec, Inc. (Salem NH) under the tradename "Mixpac."

Once the two parts have been combined, the composition should be used quickly, as the useful pot life may be short depending upon the acrylic monomer mix, the amount of complex, and the temperature at which the bonding is to be performed.

The polymerizable composition is applied to one or both substrates and then the substrates are joined together with pressure to force excess composition out of the bond line. This also has the advantage of displacing composition that has been exposed to air and that may have advanced too far in cure. In general, the bonds should be made shortly after the composition has been applied, preferably within about 10 minutes. The typical bond line thickness is about 0.1 to 0.3 mm but may exceed 1.0 mm when gap filling is needed. The bonding process can easily be carried out at room temperature and to improve the degree of polymerization it is

desirable to keep the temperature below about 40°C, preferably below 30°C, and most preferably below about 25°C.

The bonds will cure to a reasonable green strength to permit handling of the bonded components within about 1 hour. Full strength will be reached in about 24 hours under ambient conditions; post-curing with heat (typically about 80°C) may be used if desired.

The invention will be more fully appreciated with reference to the following nonlimiting examples in which (unless noted otherwise) all weights are given as weight percents (weight %), based on the total weight of the composition which is 100 weight %.

EXAMPLES

Bond Strength Test Method

The adhesive compositions described below were tested for bond strength. The base component of a given adhesive formulation (comprising a thorough mixture of thickened monomers and decomplexer) was combined with the organoborane polyamine complex (referred to as the accelerator component) and mixed with a spatula for one minute. The adhesive was then applied to a 2 inch (5.1 cm) wide, 6 inch long (15.2 cm), 8 mil (0.2 mm) thick film. The film was held flat using two 30 mil (0.8 mm) thick aluminum overlays, the overlays overlapping 0.5 inch (1.3 cm) along the entire length of each side of the film.

Each adhesive formulation was tested on two different film substrates, skived polytetrafluoroethylene (PTFE) and skived ultrahigh molecular weight polyethylene (PE). Neither of the films had any surface treatment.

Once the adhesive was applied to the first film, a second film comprising the same substrate was eased onto the adhesive using a 2.7 lb (1.2 kg) weighted glass plate. One side of the glass plate was applied to one side of the second film at an angle of about 30 degrees and then gradually lowered to a horizontal position so that the second film was applied incrementally to the first to avoid formation of bubbles in the adhesive. Sufficient adhesive was applied to the first film to provide minimum bond dimensions of 1 inch (2.5 cm) in width by 1.5 inch (3.8 cm) in length.

The bonded adherends were allowed to cure for 24 hours at room temperature (21-25°C). The samples were then tested for bond strength in the T-peel mode using an Instron Tensile Tester set at a crosshead speed of 4 inches/min (10.2 cm/min). Two overlapping free ends of the sample were clamped into the jaws of the Instron tester, one free end in the upper jaw and one free end in the lower jaw. The jaws were then pulled apart until at least 1 inch (2.5 cm) of adhesive was exposed or until adherend failure was observed. The average force per width during the run after the adhesive was initially exposed was recorded as the Peel Strength in pounds/inch width (piw).

The tensile strengths of PTFE and PE films were found to be 11 pounds/inch width (20 N/cm width) and 25 pound/inch width (44 N/cm width), respectively. Preferably, the Peel Strength values approximate the tensile strength values, indicating substrate as opposed to adhesive failure.

Solvent Resistance

Cured adhesive films were obtained by removing the thin films of cured adhesive from the adherends after the bond strength peel tests were completed. When possible, the thin film was peeled from the remaining adherend. When this was difficult, the thin film plus adherend were immersed together in tetrahydrofuran (THF) solvent, and the adhesive was later scraped off the adherend. The weight of each adhesive film was determined and is denoted as W1 below. Each adhesive was placed in a 4 ounce (118 cm³) glass jar. Sufficient THF was added to the glass jar so that the contents comprised less than 5 parts by weight cured adhesive film and more than 95 parts by weight THF. The jar was capped and placed on a roll mixer for at least 24 hours at room temperature (21-25°C). The fluid mixture was then poured into a medium mesh conical gauze/paper paint filter (available from Foremost Co. and having a weight denoted below as W2) and thoroughly rinsed with THF. Filters were dried in an 80°C forced air oven for one hour.

The filters were allowed to equilibrate overnight at room temperature before being weighed to give the value denoted below as W3. Adhesive percent solids were then calculated as follows:

$$\text{Percent Solids} = \frac{W3-W2 + 0.0299}{W1} \times 100$$

It is noted that a correction factor of 0.0299 milligrams was added to W3-W2 in the equation above to account for that portion of the filter that was lost by virtue of the process conditions.

Percent Gel was then calculated for samples of the invention by dividing the Percent Solids (calculated as described above) by the weight percent of the adhesive which is capable of addition polymerization. For those formulations whose Percent Solids never exceed 10%, the portion capable of addition polymerization is only the acrylic monomers. All other formulations include the portion derived from the acrylic monomers, the amine part of the complex and the decomplexer. A sample calculation is provided below for Example 30 of the invention:

$$\text{Percent Gel} = \frac{\text{Percent Solids} \times 100}{\text{Percent Capable of Addition Polymerization}}$$

$$\text{Percent Gel}_{\text{Ex 30}} = \frac{\text{Percent Solids}_{\text{Ex 30}} \times 100}{(\text{Wt.}\%_{\text{MMA}} + \text{Wt.}\%_{\text{BMA}} + \text{Wt.}\%_{\text{MA}} + \text{Wt.}\%_{\text{DC}} + \text{Wt.}\%_{\text{AmC}})}$$

where Wt.%_{MMA} is the weight percent of methyl methacrylate, Wt.%_{BMA} is the weight percent of butyl methacrylate, Wt.%_{MA} is the weight percent of methyl acrylate, Wt.%_{DC} is the weight percent of decomplexer, and Wt.%_{AmC} is the weight percent of the amine portion of the decomplexer used in Example 30. The Percent Solids of Example 30 can be found in Table VI to be 64.4. Example 30 comprised Initiator In-1 given in Table IV. The organoborane portion (triethylborane) has a molecular weight of 98, while the amine portion (1,6-hexanediamine) has a molecular weight of 116. Table VI indicates that the weight percent of initiator was 2.791. Thus the value of the Wt.%_{AmC} can be calculated as follows:

$$\text{Wt.}\%_{\text{AmC}} = (2.791) \frac{(116)}{(312)}$$

$$\text{Wt.}\%_{\text{AmC}} = 1.038$$

The percent Gel_{Ex30} can now be calculated from the other weight percents listed in Table VI as follows:

5

$$\text{Percent Gel}_{\text{Ex30}} = \frac{64.4 \times 100}{15.223 + 23.786 + 23.786 + 2.067 + 0.796}$$

$$\text{Percent Gel}_{\text{Ex30}} = 97.7\%$$

10

Small deviations from table values are due to rounding of Percent Solids values.

Decomplexers

Anhydride Decomplexers

15

Anhydride decomplexers of the present invention include those commercially available compounds as listed as decomplexers A-M in Table I:

TABLE I: Anhydride Decomplexers

Decomplexer	Name	Source
A	Maleic Anhydride	Aldrich Chemical Co.
B	Itaconic Anhydride	Aldrich Chemical Co.
C	Phthalic Anhydride	Aldrich Chemical Co.
D	cis-1,2,3,6-Tetrahydrophthalic Anhydride	Aldrich Chemical Co.
E	cis-1,2-Cyclohexanedicarboxylic Anhydride	Aldrich Chemical Co.
F	Isobutenylsuccinic Anhydride (K-4)	Zeeland Chemicals
G	Methacrylic Anhydride	Aldrich Chemical Co.
H	Isobutyric Anhydride	Aldrich Chemical Co.
I	Methyl Hexahydrophthalic Anhydride (MHHPA)	Milliken Chemical Co.
J	Methyl-5-norbornene-2,3-dicarboxylic Anhydride	Aldrich Chemical Co.
K	2-Octen-1-ylsuccinic Anhydride	Aldrich Chemical Co.
L	Milldride 5060 Anhydride	Milliken Chemical Co.
M	SMA-3000A Anhydride	Atochem Inc.

Preparation of Anhydride Partial Adducts

Partial adducts of poly(styrene-co-maleic anhydride) were prepared for use as decomplexers. A 50 ml glass vial was charged with 2,6-di-t-butyl-4-methylphenol (BHT) inhibitor according to the weight ratios specified in Table II. This charge was followed with charges of dried hydroxyethyl acrylate (HEA); butyl methacrylate (BMA) solvent; and poly(styrene-co-maleic anhydride) (SMA-3000A, available from Atochem Inc.), according to the weight ratios specified in Table II. The HEA had been dried over a bed of 4Å molecular sieves prior to charging.

The glass vial was sealed, shaken to mix the contents, and placed in a 105°C circulating hot air oven. After reaching a temperature of 105°C, the contents were thoroughly remixed by shaking and returned to the oven. The glass vial remained in the oven for a 10-12 hour heating cycle, during which the glass vial was shaken periodically. The anhydride adduct decomplexers included in the present invention are designated as decomplexers N-Q in Table II.

TABLE II: Anhydride Adduct Decomplexers

Decomplexer	Wt.% BHT	Wt.% HEA	Wt.% BMA	Wt.% SMA
N	0.03	3.00	49.98	46.99
O	0.03	4.89	49.98	45.10
P	0.03	5.65	49.99	44.33
Q	0.03	8.03	49.98	41.96

Comparative Decomplexer

For comparative purposes, methacrylic acid (available from Aldrich Chemical Co.) was used as a decomplexer in the following examples and has been designated as decomplexer R in Table III.

TABLE III: Comparative Decomplexer

Decomplexer	Name	Source
R	Methacrylic Acid	Aldrich Chemical Co.

Initiators

The organoborane amine complex initiators used in the present invention are listed in Table IV below. All were prepared with triethyl borane using a 1:1 boron to nitrogen ratio with the exception of the E-L-E type which used a boron to nitrogen ratio of 0.9:1. The organoborane polyamine complexes may be readily prepared using known techniques. Typically, the polyamine is combined with the organoborane in an inert atmosphere with slow stirring. An exotherm is often observed and cooling of the mixture is therefore recommended. If the ingredients have a high vapor pressure, it is desirable to keep the reaction temperature below about 70° to 80°C. Once the materials have been well mixed the complex is permitted to cool to room temperature. No special storage conditions are required although it is preferred that the complex be kept in a capped vessel in a cool, dark location. Advantageously, the complexes can be prepared in the absence of organic solvents that would later have to be removed, although they could be prepared in solvent if so desired. Solvents used in the preparation of the complexes should, preferably be ones that do not coordinate amines, for example, tetrahydrofuran or hexane.

TABLE IV: Organoborane Amine Complex Initiators

Initiator	Organoborane	Amine
In-1	Triethylborane	1,6-Hexanediamine
In-2	Triethylborane	Jeffamine ED-600 diamine ⁽¹⁾
In-3	Triethylborane	Jeffamine T-403 triamine ⁽¹⁾
In-4	Triethylborane	E-L-E diamine I ^(2a)
In-5	Triethylborane	E-L-E diamine II ^(2b)

(1) Available from Huntsman Corp.

(2) 2:1 Molar adduct of Dide Chemical Co. DCA-221 diamine and:

a = 1,6-hexanediol diacrylate

b = Shell Chemical Co. Epon 828

Adhesive Compositions (Examples 1-38 and Comparative Examples 39-41)

Two part adhesive compositions were prepared according to Table V below. The weight percent of each component based upon total composition weight is shown in this table.

The two part adhesives of this invention comprise an accelerator component and a base component. The accelerator component in all examples was solely the organoborane amine complex initiator.

5 The base component comprised a thickened acrylic monomer mixture to which has been added an effective amount of decomplexer. The thickened monomer mixture comprises a 16:25:25:34 blend by weight of methyl methacrylate (MMA), butyl acrylate (BA), methyl acrylate (MA) and poly(butyl methacrylate) (PBMA), respectively. The thickened monomer mixture components are all available from Aldrich Chemical Co.

10 Unless otherwise indicated, the standard formulation provided 3.0 moles of triethylborane for every 100 moles of free-radically polymerizable (meth)acrylate ester vinyl groups and an index of 0.75 moles of amine reactive anhydride groups for each mole of initiator amine groups.

TABLE V: Adhesive Compositions

Example	Wt. % MMA	Wt. % BMA	Wt. % MA	Wt. % PBMA	Decomplexer	Decomplexer Wt %	Initiator	Initiator Wt. %	Borane (1)	Index (2)
1	15.235	23.805	23.805	32.374	C	1.988	In-1	2.793	3.0	0.75
2	15.227	23.792	23.792	32.357	D	2.040	In-1	2.792	3.0	0.75
3	15.223	23.786	23.786	32.347	E	2.067	In-1	2.791	3.0	0.75
4	15.215	23.773	23.773	32.331	H	2.119	In-1	2.789	3.0	0.75
5	15.292	23.894	23.894	32.496	I	1.621	In-1	2.803	3.0	0.55
6	15.092	23.581	23.581	32.070	I	2.909	In-1	2.767	3.0	1.00
7	15.440	24.125	24.125	32.808	J	1.615	In-1	1.887	2.0	0.75
8	15.174	23.709	23.709	32.245	J	2.381	In-1	2.782	3.0	0.75
9	15.109	23.609	23.609	32.107	K	2.796	In-1	2.770	3.0	0.75
10	15.245	23.821	23.821	32.396	L	1.922	In-1	2.795	3.0	0.75
11	15.148	23.669	23.669	32.190	L	2.546	In-1	2.778	3.0	1.00
12	15.293	23.895	23.895	32.498	M	2.550	In-1	1.869	2.0	0.55
13	15.152	23.675	23.675	32.200	M	3.446	In-1	1.852	2.0	0.75
14	14.761	23.065	23.065	31.367	M	5.035	In-1	2.707	3.0	0.75
15	13.618	21.278	21.278	28.937	M	12.393	In-1	2.496	3.0	2.00
16	12.504	19.537	19.537	26.570	M	14.214	In-1	7.638	10.0	0.75
17	15.338	23.966	23.966	32.593	A	1.325	In-1	2.812	3.0	0.75
18	15.533	24.270	24.270	33.007	B	1.022	In-1	1.898	2.0	0.75
19	15.371	24.017	24.017	32.664	B	1.113	In-1	2.818	3.0	0.55
20	15.309	23.920	23.920	32.533	B	1.511	In-1	2.807	3.0	0.75
21	15.232	23.800	23.800	32.370	B	2.005	In-1	2.793	3.0	1.00
22	15.601	24.378	24.378	33.154	F	1.059	In-1	1.430	1.5	0.75
23	15.223	23.786	23.786	32.347	F	2.067	In-1	2.791	3.0	0.75
24	15.732	24.582	24.582	33.430	G	0.712	In-1	0.962	1.0	0.75
25	15.646	24.447	24.447	33.247	G	0.779	In-1	1.434	1.5	0.55
26	15.601	24.378	24.378	33.154	G	1.059	In-1	1.430	1.5	0.75
27	15.547	24.292	24.292	33.037	G	1.407	In-1	1.425	1.5	1.00
28	15.473	24.177	24.177	32.881	G	1.400	In-1	1.892	2.0	0.75
29	15.347	23.980	23.980	32.612	G	1.736	In-1	2.345	2.5	0.75

Example	Wt. % MMA	Wt. % BMA	Wt. % MA	Wt. % PBMA	Decomplexer	Decomplexer Wt %	Initiator	Initiator Wt. %	Borane ⁽¹⁾	Index ⁽²⁾
30	15.223	23.786	23.786	32.347	G	2.067	In-1	2.791	3.0	0.75
31	14.541	22.721	22.721	30.900	G	1.974	In-2	7.143	3.0	0.75
32	14.457	22.589	22.589	30.721	G	1.963	In-4	7.680	3.0	0.75
33	14.276	22.307	22.307	30.337	G	1.938	In-5	8.834	3.0	0.75
34	14.939	23.343	23.343	31.746	G	2.028	In-3	4.600	3.0	0.75
35	13.399	27.715	20.936	28.473	N	6.779	In-1	2.696	3.0	0.75
36	12.815	28.643	20.024	27.232	O	8.619	In-1	2.668	3.0	0.75
37	12.480	29.175	19.500	26.520	P	9.675	In-1	2.650	3.0	0.75
38	10.583	32.188	16.535	22.488	Q	15.653	In-1	2.554	3.0	0.75
Comp 39	15.280	23.875	23.875	32.470	R	1.699	In-1	2.801	3.0	1.10
Comp 40	15.186	23.728	23.728	32.271	R	2.302	In-1	2.784	3.0	1.50
Comp 41	15.070	23.548	23.548	32.025	R	3.046	In-1	2.763	3.0	2.00

(1) Moles of triethylborane/100 moles of (meth)acrylate ester vinyl groups
(2) Moles of methacrylic acid or anhydride groups/mole of initiator amine groups

Table VI: Bond Strength and Solvent Resistance

Example	Decomplexer	Bond Strength				Free Film	
		PTFE		PE		Solvent Resistance	
		piw	N/cm	piw	N/cm	% Solids	% Gel
1	C	33 ⁽¹⁾	58 ⁽¹⁾	<1	<1	0.7	1.2
2	D	30 ⁽¹⁾	53 ⁽¹⁾	2	4	1.5	2.2
3	E	25 ⁽¹⁾	44 ⁽¹⁾	<1	1	1.4	2.2
4	H	25	44	3	5	1.1	1.7
5	I	24 ⁽¹⁾	42 ⁽¹⁾	1	2	1.2	2.0
6	I	16 ⁽¹⁾	28 ⁽¹⁾	<1	<1	1.4	2.2
7	J	24 ⁽¹⁾	42 ⁽¹⁾	8	14	1.1	1.7
8	J	31 ⁽¹⁾	54 ⁽¹⁾	7	12	1.2	1.8
9	K	24 ⁽¹⁾	42 ⁽¹⁾	1	2	0.9	1.4
10	L	11	20	9	16	1.2	1.8
11	L	15	26	8	13	0.8	1.2
12	M	6	11	22	39	ND	ND
13	M	13	22	21	37	ND	ND
14	M	12	21	16	27	2.4	4.0
15	M	11	19	16	28	ND	ND
16	M	11	20	6 ⁽¹⁾	11 ⁽¹⁾	ND	ND
17	A	29 ⁽¹⁾	51 ⁽¹⁾	<1	<1	35.2	53.6
18	B	24 ⁽¹⁾	42 ⁽¹⁾	5	9	44.0	66.8
19	B	19 ⁽¹⁾	33 ⁽¹⁾	7	12	28.7	43.8
20	B	17 ⁽¹⁾	29 ⁽¹⁾	5	9	61.4	93.5
21	B	13	23	2	3	50.4	76.5
22	F	21 ⁽¹⁾	37 ⁽¹⁾	11 ⁽¹⁾	18 ⁽¹⁾	41.0	62.1
23	F	32 ⁽¹⁾	56 ⁽¹⁾	2	4	43.9	66.6
24	G	<1	1	16	27	57.8	87.7
25	G	8	15	19 ⁽¹⁾	33 ⁽¹⁾	59.1	89.7
26	G	13	23	8	14	57.6	87.4
27	G	16 ⁽¹⁾	28 ⁽¹⁾	7	13	63.0	95.3
28	G	18 ⁽¹⁾	31 ⁽¹⁾	3	5	60.8	92.2
29	G	19 ⁽¹⁾	32 ⁽¹⁾	<1	<1	61.5	93.3
30	G	21 ⁽¹⁾	37 ⁽¹⁾	1	2	64.4	97.7
31	G	28 ⁽¹⁾	49 ⁽¹⁾	7	12	60.1	89.1
32	G	30 ⁽¹⁾	53 ⁽¹⁾	22 ⁽¹⁾	39 ⁽¹⁾	60.1	89.1
33	G	10	18	23	40	54.5	80.3
34	G	25 ⁽¹⁾	44 ⁽¹⁾	<1	<1	62.8	94.3
35	N	12	20	14	24	14.0	20.1
36	O	8	15	10	18	31.2	43.8
37	P	9	16	10	18	36.7	51.1
38	Q	5	9	5	9	48.9	64.5

Example	Decomplexer	Bond Strength				Free Film	
		PTFE		PE		Solvent Resistance	
		piw	N/cm	piw	N/cm	% Solids	% Gel
Comp 39	R	7	12	4 ⁽¹⁾	6 ⁽¹⁾	1.3	2.0
Comp 40	R	9	16	4 ⁽¹⁾	6 ⁽¹⁾	2.0	3.1
Comp 41	R	11 ⁽²⁾	19 ⁽²⁾	6 ⁽³⁾	10 ⁽³⁾	0.4	0.6

ND = Not determined

(1) Adherend tore

(2) 1 inch (2.5 cm) wide adherend

(3) 15 mil (0.4 mm) thick PE used

Each bond strength value in Table VI is the average reading in pounds per inch width (piw) or Newtons per centimeter (N/cm) over the length of the bond which was pulled. In general, preferred bond strengths are at least 5 piw (9 N/cm).

- 5 The data in Table VI indicate good to outstanding bond formation for all of the formulations on either PE and PTFE, and for many formulations on both PE and PTFE.

- 10 The data of Table VI also show that decomplexers of the present invention can advantageously provide both a reduced level of mobile constituents and improved solvent resistance compared to the comparative decomplexer (methacrylic acid). More specifically, Examples 17-38 provided % Solid values in the range of 14 to 64 and % Gel values in the range of 20 to 98, while the Comparative Examples 39-41 provided % Solid values in the range of 0.4-2.0 and % Gel values in the range of 0.6-3.1.

- 15 It is noted that the decomplexers of Examples 17-38 comprised free radically polymerizable groups (namely, 1,1-disubstituted alkenes and 1,2-disubstituted alkenes which are part of an α , β -unsaturated carbonyl structure). Such decomplexers are capable of covalently bonding with the polyamine portion of the organoborane amine complex to form decomplexer-amine reaction products
- 20 comprising more than one free radically polymerizable group. As a consequence, these decomplexers provide adhesive compositions having both a reduced level of mobile constituents and good solvent resistance. Such decomplexers are preferred for the present invention.

It is further noted that the decomplexer of Comparative Examples 39-41 (methacrylic acid) comprised a 1,1-disubstituted alkene group which is capable of ionically (as opposed to covalently) bonding with the polyamine portion of the organoborane amine complex. As a consequence, this decomplexer was unable to provide solvent resistance.

Other observations from the data of Table VI include the following: Examples 24-29 illustrate that the initiator and anhydride concentrations can be independently varied to optimize adhesive bond strengths without adversely affecting solvent resistance. Examples 30-34 illustrate that a variety of organoborane amine complexes may be utilized with the decomplexers of the invention to provide excellent adhesive bond strength values and solvent resistance.

Various modifications and alterations of this invention will become apparent to those skilled in the art without departing from the scope and spirit of the invention. It should be understood that this invention is not limited to the illustrative embodiments set forth herein.

CLAIMS

The embodiments for which an exclusive property or privilege is claimed are defined as follows:


5

1. An initiator system capable of initiating the polymerization of acrylic monomers comprising (1) an organoborane amine complex and (2) a decomplexer comprising at least one anhydride group.

2. An initiator system according to Claim 1 wherein said decomplexer
10 comprises at least one free radically polymerizable group.


3. An initiator system according to Claim 1 wherein said decomplexer comprises at least one free radically polymerizable group and said organoborane amine complex comprises at least two amine groups.

4. An initiator system according to Claim 1 wherein said decomplexer
15 has the structure:



wherein each R₁ and R₂ are independently selected from the group consisting of aliphatic, cycloaliphatic and aromatic groups.

20 5. An initiator system according to Claim 1 wherein said decomplexer has the following structure:




wherein R₃ is a divalent organic radical.

6. An initiator system according to Claim 1 wherein said decomplexer is selected from the group consisting of methacrylic anhydride, itaconic anhydride, maleic anhydride and isobutenyl succinic anhydride.

7. An initiator system according to Claim 1 wherein said organoborane amine complex comprises at least two amine groups.

8. An initiator system according to Claim 1 wherein said complex has the structure:




wherein R_8 is selected from the group consisting of alkyl groups having 1 to 10 carbon atoms; R_9 and R_{10} are independently selected from the group consisting of alkyl groups having 1 to 10 carbon atoms and phenyl-containing groups; the value of v is selected so as to provide a 0.5:1 to 4:1 ratio of primary or secondary amine nitrogen atoms to boron atoms in the complex; and Am is an amine.

9. A polymerizable acrylic composition comprising:

- a) at least one acrylic monomer;
- b) an effective amount of an organoborane amine complex; and
- c) an effective amount of a decomplexer comprising at least one anhydride group, said decomplexer being reactive with said amine to liberate the organoborane to initiate polymerization of the at least one acrylic monomer.


10. A polymerizable acrylic composition according to Claim 9 wherein said decomplexer comprises at least one free radically polymerizable group and said organoborane amine complex comprises at least two amine groups.

11. A polymerizable acrylic composition according to Claim 9 wherein said decomplexer has the structure:



wherein each R_1 and R_2 are independently selected from the group consisting of aliphatic, cycloaliphatic and aromatic groups.

12. A polymerizable acrylic composition according to Claim 9 wherein
5 wherein said decomplexer has the following structure:



wherein R_3 is a divalent organic radical.

13. A polymerized acrylic adhesive composition according to Claim 9.
14. A bonded composite comprising a first substrate, a second substrate
10 and a polymerized acrylic adhesive composition according to Claim 9 that adhesively bonds the first and second substrates together.
15. A method of initiating the polymerization of at least one acrylic monomer, the method comprising the steps of:
- a) providing at least one acrylic monomer;
 - b) blending the at least one acrylic monomer with the
15 components of a polymerization initiator system, said system comprising:
 - i) an organoborane amine complex,
 - ii) an effective amount of a decomplexer comprising at
20 least one anhydride group, said decomplexer being reactive with amine for liberating the organoborane to initiate polymerization of the at least one acrylic monomer; and
 - c) initiating polymerization of the at least one acrylic monomer.
- 25 16. A method of increasing the solvent resistance of a polymerized acrylic adhesive composition obtained by organoborane-initiated polymerization of acrylic monomer, said method comprising the steps of

5

- a) providing at least one acrylic monomer;
- b) providing an organoborane amine complex comprising at least two amine groups;
- c) providing a decomplexer comprising at least one anhydride group and at least one free radically polymerizable group;
- d) blending components a), b) and c), and;
- e) initiating polymerization of the at least one acrylic monomer and continuing polymerization until a solvent resistant acrylic adhesive composition is obtained.

10

INTERNATIONAL SEARCH REPORT

Internat Application No
PCT/US 96/15706

A. CLASSIFICATION F SUBJECT MATTER
IPC 6 C08F20/12 C09J4/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08F C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,95 22567 (MINNESOTA MINING AND MANUFACTURING CO.) 24 August 1995 ---	
A	US,A,5 106 928 (M. SKOULTCHI) 21 April 1992 cited in the application ---	
A	EP,A,0 561 352 (NATIONAL STARCH AND CHEMICAL INVESTMENT HOLDING CORP.) 22 September 1993 cited in the application ---	
A	US,A,5 310 835 (M. SKOULTCHI) 10 May 1994 cited in the application -----	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

23 January 1997

Date of mailing of the international search report

- 5. 02. 97

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Cauwenberg, C

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat	Application No
PCT/US 96/15706	

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9522567	24-08-95	AU-A- 2971695	04-09-95
		EP-A- 0746573	11-12-96
		US-A- 5539070	23-07-96

US-A-5106928	21-04-92	DE-D- 69201093	16-02-95
		DE-T- 69201093	11-05-95
		EP-A- 0511464	04-11-92
		ES-T- 2067965	01-04-95
		HK-A- 51195	13-04-95
		JP-A- 5098216	20-04-93
		JP-B- 7072264	02-08-95
		KR-B- 9509549	24-08-95
		US-A- 5143884	01-09-92

EP-A-561352	22-09-93	US-A- 5286821	15-02-94
		AU-A- 3305493	21-10-93
		CA-A- 2091701	18-09-93
		JP-A- 6093235	05-04-94
		JP-B- 7116249	13-12-95
		KR-B- 9608486	26-06-96
		US-A- 5376746	27-12-94

US-A-5310835	10-05-94	NONE	
